

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 06-172007

(43)Date of publication of application : 21.06.1994

(51)Int.Cl. C04B 28/34
A61K 6/033
A61L 27/00

(21)Application number : 04-328185

(71)Applicant : MITSUBISHI MATERIALS CORP

(22)Date of filing : 08.12.1992

(72)Inventor : HIRANO MASAHIRO
TAKEUCHI HIROYASU

(54) HIGH-STRENGTH CEMENT OF CALCIUM PHOSPHATE

(57)Abstract:

PURPOSE: To obtain a high-strength cement of calcium phosphate having workability not reducing even by blending in high powder liquid ratio and high strength and neither irritation to organism nor deterioration.

CONSTITUTION: High-strength cement of calcium phosphate comprises 90-70wt.% α type calcium tertiary phosphate, 5-25wt.% calcium quaternary phosphate and 5-10wt.% calcium secondary phosphate.

LEGAL STATUS

[Date of request for examination] 25.05.1995

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 2776179

[Date of registration] 01.05.1998

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]